

AMTEX® PLUS FLAME RESISTANT FABRICS

GOVERNMENT CERTIFIED TESTING LAB

ASTM D 6413 VERTICAL FLAME TEST

GUARANTEED FLAME RESISTANCE

FOR THE LIFE OF THE GARMENT

FABRICS THAT MEET

NFPA 70 E

NFPA 2112

UNDERWRITERS LAB CERTIFICATION

ASTM F1506

ASTM D4108

FOR GARMENTS ACCEPTABLE UNDER

OSHA 1910.269

PYROMAN MANIKIN TESTING

ASTM 1930

TEST CONDUCTED BY

NORTH CAROLINA STATE UNIVERSITY

COLLEGE OF TEXTILES

RALEIGH, NC

ELECTRIC ARC EXPOSURE TESTING

ASTM F 1959

TEST CONDUCTED BY

KINECTRICS

HIGH CURRENT LABORATORY

TORONTO, CANADA

OUR STYLE	XCYE
DESCRIPTION	9.0 oz/sy
	88% COTTON / 12% NYLON C/N
	3/1 LHT
OUR NAME	CHEYENNE TWILL
TEST	BOTTOM
CONSTRUCTION	92 x 45
WARP YARNS	14 RS CTN/NY
FILLING YARNS	9.4 RS CTN
WIDTH (CUTTABLE)	63.00
AVERAGE WEIGHT oz/sy	9.6
WARP TENSILE LBS	160
FILL TENSILE LBS	110
WARP TEAR LBS	10
FILL TEAR LBS	13.0
WARP FLEX	20,000
FILL FLEX	5000
WARP SHRINKAGE 10 IL AVG	3.5
FILL SHRINKAGE 10 IL AVG	3.5
ATPV RATING cal/cm²	12.2 – CATEGORY 2
CHAR LENGTH (AVG 100 IL)	3"
ASTM 1506	YES
CAN/CGSB	YES
U/L 2112 APPROVAL	YES